

AMENDMENTS TO THE CLAIMS

This listing of claims will replace all prior versions and listings of claims in the application.

Listing of Claims:

1. **(Currently Amended)** A molded composite article in which a resin member comprising a non-urethane thermoplastic resin and a resin member comprising a thermoplastic polyurethane resin are directly ~~joined~~ bonded with each other, wherein

the non-urethane thermoplastic resin is a non-urethane thermoplastic resin (Ib) which is (Ib-1) a polyamide resin comprising a polyamide component having an alicyclic ring and contains a terminal amino group in a concentration of not less than 15 mmol/kg, wherein a part of or all the terminal amino group is an alicyclic amino group, or (Ib-2) a resin composition comprising a non-urethane thermoplastic resin and an amino group-containing compound,

the non-urethane thermoplastic resin (Ib) has an amino group in a concentration of not less than 15 mmol/kg,

in the polyamide resin (Ib-1), the polyamide component having an alicyclic ring is at least one member selected from the group consisting of

an alicyclic polyamide resin,

an alicyclic polyamide elastomer, and

a polyamide component having an alicyclic ring comprising an alicyclic polyamide component and a non-alicyclic polyamide component, wherein said alicyclic polyamide component is at least one member selected from the group consisting of an alicyclic polyamide resin, an alicyclic polyamide elastomer and an alicyclic polyamide oligomer; and said non-alicyclic polyamide component is at least one member selected from the group consisting of an aliphatic polyamide resin and an aromatic polyamide resin,

in the resin composition (Ib-2), the non-urethane thermoplastic resin comprises at least one member selected from the group consisting of a polyamide resin, a polyester resin, a polycarbonate resin, and a polyphenylene sulfide resin,

the amino group-containing compound is a polyamide oligomer having a number average molecular weight of 2000 to 9000, and

the thermoplastic polyurethane resin is a thermoplastic polyurethane elastomer.

2-5. (Canceled)

6. (Previously Presented) A molded composite article according to Claim 1, wherein in the non-urethane thermoplastic resin (Ib-1), the polyamide component having an alicyclic ring is obtained by using an alicyclic diamine as a diamine component.

7. (Previously Presented) A molded composite article according to Claim 1, wherein the non-urethane thermoplastic resin (Ib) is the non-urethane thermoplastic resin (Ib-1) comprising a polyamide resin, and the proportion (molar ratio) of an alicyclic monomer residue relative to other monomer residue in all polyamide components constituting the polyamide resin is 100/0 to 0.1/99.9.

8. (Previously Presented) A molded composite article according to Claim 1, wherein the non-urethane thermoplastic resin (Ib) is the resin composition (Ib-2).

9. (Previously Presented) A molded composite article according to Claim 1, wherein in the resin composition (Ib-2), the amino group-containing compound has a plurality of primary amino groups in the molecule.

10. (Previously Presented) A molded composite article according to Claim 1, wherein in the resin composition (Ib-2), the amino group-containing compound has an amino group in a concentration of 40 to 1000 mmol/kg.

11. **(Previously Presented)** A molded composite article according to Claim 1, wherein in the resin composition (Ib-2), the amino group-containing compound has an amino group in a concentration of 50 to 700 mmol/kg.

12. **(Previously Presented)** A molded composite article according to Claim 1, wherein the non-urethane thermoplastic resin (Ib) is the resin composition (Ib-2), and the proportion of the amino group-containing compound is 0.01 to 20 parts by weight relative to 100 parts by weight of the non-urethane thermoplastic resin.

13. **(Previously Presented)** A molded composite article according to Claim 1, wherein the non-urethane thermoplastic resin (Ib) is the resin composition (Ib-2) and the non-urethane thermoplastic resin is at least one selected from the group consisting of a polyamide resin, a polyester resin, and a polyphenylene sulfide resin.

14. **(Previously Presented)** A molded composite article according to Claim 1, wherein the resin member comprising the non-urethane thermoplastic resin (Ib) is directly joined to the resin member comprising at least one thermoplastic polyurethane resin selected from the group consisting of a polyester urethane elastomer and a polyether urethane elastomer.

15-18. **(Canceled)**

19. **(Original)** A molded composite article according to Claim 1, which is a shoe member or a roll member.

20-21. **(Canceled)**

22. **(Withdrawn)** A process for producing a molded composite article recited in claim 1, which comprises

heating at least one resin selected from the group consisting of the non-urethane-series thermoplastic resin and the thermoplastic polyurethane-series resin, and
joining the both resins with each other.

23. **(Withdrawn)** A process according to Claim 22, which comprises
heating at least one resin selected from the group consisting of the non-urethane-series thermoplastic resin and the thermoplastic polyurethane-series resin to be molten, bringing at least one resin in the molten state into contact with the other resin, and
joining both resins with each other.

24. **(Withdrawn)** A process according to Claim 22, wherein the non-urethane-series thermoplastic resin and the thermoplastic polyurethane-series resin are joined with each other in the molding process by a molding method selected from the group consisting of a thermoforming, an injection molding, an extrusion molding, and a blow molding.

25. **(Canceled)**